


Attorney Docket No.: KKP-0276



CERTIFICATION OF THE TRANSLATION

I, **Eri Hoshino**, 3-3-1103, 3-chome, Omotemachi, Nagaoka, Niigata, certify that I am familiar with both the Japanese and English languages, that I have reviewed both the specification of the above identified application as filed in Japanese and the attached English language translation thereof, and that the English translation is a true, faithful and exact translation of the certified copy of Japanese Patent Application No. **2003-084878** filed with the Japanese Patent Office on **March 26, 2003**.

January 23, 2008


Eri Hoshino



[Document Name] Specification

[Title of the Invention] WATER BASED INK FOR BALL-POINT PEN AND BALL-POINT PEN USING THE SAME

[Claim]

5 1. Water based ink for ball-point pen comprising a solvent formed by a water and an alcoholic solvent having a vapor pressure at 20°C of 0.5 kPa or higher, a pigment constituting a coloring material, and a water-soluble resin constituting a writing fixing agent, wherein an ink viscosity at 20°C is within a range of 5 to 30 mPa·s.

10 2. Water based ink for ball-point pen according to claim 1, wherein the water-soluble resin is present by 5 to 20 mass% with respect to a total amount of the ink composition.

 3. Water based ink for ball-point pen according to claim 1 or 2, wherein the water-soluble resin is an acrylic resin.

15 4. Water based ink for ball-point pen according to claim 3, wherein the acrylic resin has a molecular weight of 5000 to 20000, a glass transition point of 40 to 150°C and an acid value of 50 to 250.

 5. Water based ink for ball-point pen according to one of claims 1 to 4, wherein the solvent formed by a water and the alcoholic
20 solvent constitutes 60 to 90 mass% of the entire amount of the ink composition, and the alcoholic solvent constitutes 5 to 15 mass% of the entire amount of the ink composition.

 6. Water based ink for ball-point pen according to one of claims 1 to 5, wherein the pigment constitutes 1 to 10 mass% of the entire
25 amount of the ink composition.

7. Ball-point pen including, at a tip portion of an ink tube, a ball-point pen tip rotatably supporting a ball either directly or across a tip holder, wherein an ink according to one of claims 1 to 6 is directly filled in the ink tube.

5 8. Ball-point pen according to claim 7, wherein the ball-point pen tip includes a valve mechanism where the ball, rotatably supported in the pen tip, is pressed to an internal wall of a pen tip ridge by a coil spring disposed in pressure contact with a rear end of the ball either directly or across a pressing member while not in use, and a gap is formed
10 between the internal wall of the pen tip ridge and the ball by a thrust applied at a writing thereby allowing the ink to flow out.

9. Ball-point pen according to claim 7 or 8, wherein the ink tube is provided with an ink following member, in contact with an ink surface at a tail portion opposite to a mounting part at the front tip
15 for writing.

10. Ball-point pen according to one of claims 7 to 9, wherein the ball pen tip is formed by a stainless steel material and the ball has an arithmetic mean surface roughness of 5 nm or less.

11. Ball-point pen according to one of claims 7 to 10, adapted
20 for use on a non-permeable writing surface.

[Detailed Explanation of the Invention]

[0001]

[Technical Field]

The present invention relates to a water based ink for ball-point
25 pen having a novel function and ball-point pen using the same, and more

particularly to a water based ink for ball-point pen capable of writing on a non-permeable surface such as metal, glass or plastics and ball-point pen using the same.

[0002]

5 [Prior Art]

As a writing utensil capable of writing on a permeable surface such as a paper surface, a ball-point pen, having a ball-point pen tip rotatably supporting a ball at a tip portion of an ink tube, is already well known.

On the other hand, as a writing utensil capable of writing on a
10 non-permeable surface such as metal, glass or plastics, there is known a marking pen having a pen tip generally formed by a fiber bundle. The marking pen is generally classified into a water based type employing a water-based solvent and an oil based type employing an oily solvent, and is widely employed for writing bold characters or writing on the
15 aforementioned non-permeable surface, but such marking pen is associated with two inherent drawbacks.

A first drawback is that the pen tip, being formed by a fiber bundle, is very easily deformed or broken. The pen tip formed by the fiber bundle realizes a planer contact with the surface to be written, thus enabling
20 a writing of a bold character. Also in case of writing on a non-permeable surface, the ink can be coated sufficiently according to the movement of the pen tip since a ball rotation as in the ordinary ball-point pen is not involved. However a fiber bundle is easily broken or deformed at the tip portion by writing, and cannot guarantee a constant writing width over
25 a prolonged use. The pen tip formed by the fiber bundle tends to be

deformed particularly in case of writing on a non-permeable surface such as of metal, glass or plastics harder than a paper surface.

A second drawback is that, because a volatile ink is generally employed, the writing becomes impossible when the pen is left uncapped even for a short period. The marking pen employs a pen tip formed by a fiber bundle as explained above, and is designed to discharge an extremely larger amount of ink from the pen tip in comparison with a ball-point pen, in order to realize satisfactory writing of a bold character or on a non-permeable surface. The marking pen is characterized by employing a volatile ink to appropriately cope with the problems of the drying of writing, blotting of writing and penetration of writing to the rear side. On the other hand, the ink contained in the fiber bundle of the pen tip is in an exposed state, and shows a rapid viscosity increase or solidification upon drying-up, whereby the writing becomes impossible.

A recent invention proposes a surface treatment on the fiber bundle to extend the service life, but a cautious attention is always required for the ink viscosity because the ink flows by a capillary action in the entire ink flow path from an ink adsorbent member to the fiber bundle at the pen tip.

An oily ink for ball-point pen utilizing a dye is disclosed for example in JP-A Nos. 2002-226760 and 2002-36775. However, such inks have low covering power and low resistance to the exposure to sunlight because of the use of a dye, and the writing may fade out when the ink is used in an outdoor environment.

The marking pen has been employed widely, but involves inherent

drawbacks in the factors providing advantageous effects as explained in the foregoing, thus leading to limitations in the use.

Also an ordinary aqueous ball-point pen cannot write on a non-permeable surface such as metal, glass or plastics.

5 As explained above, the marking pen and the ordinary ball-point pen are still defective in the writing on the non-permeable surface.

[Patent Document 1] Japanese Patent Unexamined Publication (JP Kokai) 2002-226760

[Patent Document 2] Japanese Patent Unexamined Publication (JP Kokai) 10 2002-36775

[0003]

[Problems to be Solved by the Invention]

In order to resolve the aforementioned inherent drawbacks of the marking pen, there have been made various attempts to form the pen tip, instead of utilizing the fiber bundle, with a ball-point pen tip formed by metal or a resinous material as in the ball-point pen. However, use of the metal or resinous material for the pen tip in accordance with a mere replacement of the marking pen structure with the ball-point pen structure cannot completely eliminate the aforementioned drawbacks but results in a new drawback. More specifically, on a non-permeable surface for example metal, glass or plastics, the ball does not rotate because a resistance on the surface of a ball receiving seat in the pen tip is larger than a resistance on the writing surface. In case such relationship stands on the ball, the ball cannot rotate because of the lack of a rotating force on the ball. Unless the ball can rotate, the 25

ink does not flow out from the pen tip, so that satisfactory writing cannot be expected.

In case of the marking pen utilizing the fiber bundle for the pen tip, a uniform and thin ink film is transferred onto the writing surface because the pen tip is in planar contact with the writing surface. On the other hand, from the pen tip of a metal or a resinous material having a rotatable ball, the ink is not transferred as a thin and uniform film onto the writing surface but as a thick film because the contact between the ball and the writing surface is constituted by a continuation of point contacts. A thick ink film formed on the non-permeable surface tends to show a peeling after drying, and does not provide a satisfactory fixing property for the writing. Also in case of writing on a paper surface, an ink film discharged thicker than in the marking pen aggravates the rear penetration or the blotting of the writing.

As explained in the foregoing, various investigations have been made to improve the damage of the pen tip and the drying-up of the ink which are the inherent drawbacks of the marking pen, but none has realized a completely satisfactory performance.

The present invention is to provide an ink for a ball-point pen capable of satisfactory writing without being restricted by the properties of the writing surface, also being satisfactory in a fixing property, a covering power and a fastness, free from a rear penetration or a blotting of the writing on paper, and further capable of preventing ink drying on the pen tip, and a ball-point pen utilizing such ink. The present inventor, according to the invention, provides an ink for a ball-point pen, that

not only resolves the inherent drawbacks of the conventional marking pen but also enables the writing on the non-permeable surface not achievable with a ball-point pen, thereby greatly expanding the application of the ordinary ball-point pen, and a ball-point pen utilizing such ink.

5 [0004]

[Means for Solving the Problems]

The present invention provides:

1. A water based ink for ball-point pen that includes a solvent formed by a water and an alcoholic solvent having a vapor pressure at 20°C
10 of 0.5 kPa or higher, a pigment constituting a coloring material, and a water-soluble resin constituting a writing fixing agent, and has an ink viscosity at 20°C of 5 - 30 mPa.s.

2. The water based ink for ball-point pen as described in the above aspect 1, wherein the water soluble resin may be present by 5 - 20 mass%
15 with respect to a total amount of the ink composition.

3. The water based ink for ball-point pen as described in the above aspect 1 or 2, wherein the water-soluble resin may be an acrylic resin.

4. The water based ink for ball-point pen as described in the above aspect 3, wherein the acrylic resin may have a molecular weight of 5000
20 to 20000, a glass transition point of 40 to 150°C and an acid value of 50 to 250.

5. The water based ink for ball-point pen as described in one of the above aspects 1 to 4, wherein the solvent formed by water and the alcoholic solvent may constitute 60 to 90 mass% of the entire amount of
25 the ink composition, and the alcoholic solvent may constitute 5 to 15 mass%

of the entire amount of the ink composition.

6. The water based ink for ball-point pen as described in one of the above aspects 1 to 5, wherein the pigment may constitute 1 to 10 mass% of the entire amount of the ink composition.

5 7. A ball-point pen that includes, at a tip portion of an ink tube, a ball-point pen tip rotatably supporting a ball either directly or across a tip holder, wherein the ink as described in one of the above aspects 1 to 6 is directly filled in the ink tube.

10 8. The ball-point pen as described in the above aspect 7, wherein the ball-point pen tip may include a valve mechanism where the ball, rotatably supported in the pen tip, is pressed to an internal wall of a pen tip ridge by a coil spring disposed in pressure contact with a rear end of the ball either directly or across a pressing member while in no use, and a gap is formed between the internal wall of the pen tip ridge
15 and the ball by a thrust applied at a writing thereby allowing the ink to flow out.

20 9. The ball-point pen as described in the above aspect 7 or 8, wherein the ink tube may be provided with an ink following member, in contact with an ink surface at a tail portion opposite to a mounting part at the front tip for writing.

10. The ball-point pen as described in one of the above aspects 7 to 9, wherein the ball-point pen tip may be formed by a stainless steel material and the ball has an arithmetic mean surface roughness of 5 nm or less.

25 11. The ball-point pen as described in one of the above aspects

7 to 10, which may be used on a non-permeable writing surface.

The ink viscosity in the invention is measured with a viscosimeter Model B8M, manufactured by Tokimec Co., at a revolution of a BL rotor of 12 rpm and under an environment of 20°C.

5 The ink tube in the invention refers to a cartridge of a ball-point pen refill accommodatable in the shaft tube or the shaft tube itself when the ink is filled directly in the shaft tube, and is not restricted in the material or the structure as long as the ink tube is provided at a front tip portion with a ball-point pen tip rotatably supporting a ball.

10 [0005]

[Mode for Carrying Out the Invention]

 According to the present invention, the ink has a viscosity of 5 – 30 mPa·s under a measuring environment of 20°C. As explained in the foregoing, in writing on a non-permeable surface, the writing surface is
15 often extremely smooth, thus hardly generating a driving force for causing rotation of the ball in the pen tip. As a result of intensive investigation, the present inventor finds that a prompt formation of an ink film on the ball surface in writing generates a situation where the ball can rotate even on a smooth writing surface. Although scientific
20 clarification is not yet enough, the inventor estimates that there is a combined effect of a reduction of a rotation resistance by an ink filling of lubricating property around the ball receiving seat, and a formation of a wet rotation environment by the transfer of viscous ink onto the smooth writing surface.

25 The ink viscosity of less than 5 mPa·s under a measuring environment

of 20°C enables satisfactory writing on a smooth non-permeable surface, but is unable to prevent a blotting or a rear penetration of the writing in case of writing on a paper surface. Also at viscosities exceeding 30 mPa-s, a prompt ink film formation is not realized on the ball surface at
5 the writing, and a satisfactory writing cannot be achieved on a smooth non-permeable surface.

[0006]

The invention employs a pigment as the coloring material. The pigment is very advantageous as it can provide a writing of a high covering
10 power on a non-permeable surface. Also, in comparison with a dye, the pigment has a higher resistance for example to the exposure to sunlight, and is advantageous also in the use in an outdoor environment.

Also, as the pigment forms a dried film extremely rapidly in a small gap formed between a pen tip member and the ball, there is provided an effect that the drying-up of the ink does not proceed into the interior
15 of the pen tip member. A dry film forming property of the pigment, in case of a pen tip formed with a fiber bundle, inhibits the capillary action thereby causing a major difficulty in the ink flow. On the other hand, also in a ball-point pen provided with a ball-point pen tip formed by a
20 metal or a resinous material, a writing failure is induced in case the drying-up proceeds into the interior of the pen tip. Based on the foregoing, the invention most efficiently prevents the writing failure caused by the ink drying-up by a combination of a ball-point pen tip formed with a metal or a resinous material and an ink utilizing a pigment of a
25 high dry film forming property. A satisfactory writing can be realized

by limiting the ink viscosity as explained in the foregoing. The dry film formation in the gap of the pen tip could also be realized by adding for example a polymer component in the ink composition, but, in consideration of the limitation in the ink viscosity, it is possible to most efficiently achieve a satisfactory writing and solve the problem of a drying-up by employing a pigment as the coloring material added as an essential component. The pigment can be an organic pigment, an inorganic pigment or a modified pigment, such as carbon black, or a pigment of phthalocyanine type, azo type, quinacridone type, quinophthalone type, threne type or triphenylmethane type.

[0007]

The invention employs, as a solvent, water and an alcoholic solvent having a vapor pressure at 20°C of 0.5 kPa or higher. In the invention, the solvent is expected to exhibit functions of maintaining dispersion of the pigment and regulating volatility. The present inventor experimentally finds that a combination of water and an alcoholic solvent having a vapor pressure at 20°C of 0.5 kPa or higher is most effective. The content of a water and the alcoholic solvent is variable by a desired ink viscosity and other present components, however it is preferably 60 to 90 mass% with respect to the entire mass of the ink composition. When the content is less than 60 mass%, it is difficult to control the drying-up of the pen tip because of the low content of the solvent, while contents exceeding 90 mass% result, because of the large amount of the solvent, in a slow drying of the writing and tend to cause a deterioration of the fixing property and a blotting of the writing. The content of the

alcoholic solvent having a vapor pressure at 20°C of 0.5 kPa or higher is also variable according to the kind of the selected pigment, however it is preferably 5 to 15 mass% with respect to the entire mass of the ink composition. The content of less than 5 mass% results in a slow drying of the writing, thus causing a rear penetration or a blotting of the writing depending on the paper. Also an effective film formation is delayed in the gap of pen tip, so that the drying-up of the ink may proceed into the interior of the pen tip in a certain environment of standing, thus resulting in a writing failure at the start of writing. The contents exceeding 15 mass% may deteriorate the dispersion stability of the pigment depending on the polarity of the solvent, whereby the usable pigment becomes undesirably restricted. Also an ink evaporation from the surface of an ink tank becomes conspicuous, so that the ink tank is restricted in a material or a designing thereof. The alcoholic solvent employable in the invention is determined in consideration of matching with the pigment, but preferred examples of the alcoholic solvent include methanol, ethanol, 1-propanol, 2-propanol, 1-butanol, 2-butanol and t-butanol. It is also possible to select and use two or more of such alcoholic solvents in combination.

20 [0008]

The invention employs a water-soluble resin for the purpose of improving a fixing property of the writing on a non-permeable surface. Though the pigment employed as the coloring material has a film forming property, in order to provide the writing with the abrasion resistance, it is necessary to blend a film forming agent also in view of an adhesion

to the writing surface. However, also in this case, in consideration of the limitation in the ink viscosity, it is necessary to avoid selecting a resinous component which will increase the viscosity when dissolved in the ink. Also a dispersing agent becomes indispensable in order to maintain a stable dispersion of the pigment which is an essential component. A water-soluble resin having a dispersing ability and a fixing ability at the same time could provide a most efficient formulation in constructing an ink composition having a restriction in viscosity. The applicable a water-soluble resin is represented by an acrylic resin, which is a preferred water-soluble resin having the pigment dispersing ability and the fixing property after drying. The water-soluble resin has to be selected in consideration of the ink viscosity in addition to the dispersing ability and the fixing property as explained before. A larger content of the water-soluble resin improves the fixing property, but, in consideration of the ink viscosity, a content of 5 to 20 mass% with respect to the entire mass of the ink composition is most advantageous. When the content is less than 5 mass%, it is difficult to realize a satisfactory fixing property of the writing on a non-permeable surface, while the content of more than 20 mass% tends to result in an increase in the ink viscosity and makes it difficult to realize a satisfactory writing-starting performance since a strong dried film is formed in the pen tip portion. The use of the water-soluble resin in such large amount is also one of the features of the present invention.

The usable water-soluble resin other than the acrylic resin can be, for example, an alkyd resin, a cellulose derivative,

polyvinylpyrrolidone, or polyvinyl alcohol.

[0009]

In case of employing an acrylic resin, it is desirable to select a grade having a molecular weight from 5000 to 20000, a glass transition point from 40 to 150°C, and an acid value from 50 to 250. As already explained in detail, one of the features of the invention is to prevent drying of the pen tip by employing a ball-point pen tip formed by a metal or a resinous material at the pen tip, adopting a volatile ink, and forming a suitable dry ink film after drying. Also the realized effects include an improvement of the fixing property on the non-permeable surface by such dry film. In case of acrylic resin, the molecular weight of less than 5000 cannot form a satisfactory dry film, and a high fixing property on the non-permeable surface cannot be expected. Also with the molecular weight exceeding 20000, the dry film at the pen tip becomes excessively strong, whereby a writing failure at the start of writing tends to be generated. Also the glass transition point of less than 40°C tends to generate a softer film after drying, so that a satisfactory drying of the writing is difficult to obtain on the non-permeable surface. The glass transition point exceeding 150°C tends to generate a harder film after drying, so that the fixing property of the writing is undesirably impaired. The acid value of less than 50 makes it difficult to provide a stable ink because the solubility in water is lowered. Also the acid value exceeding 250 excessively increases the compatibility in a water, thus impairing the water resistance of the writing. The present inventor defined the preferable ranges experimentally in order to resolve the aforementioned

drawbacks and to attain the objectives.

The characteristics of the water-soluble resin to be employed are those as explained before, however the water-soluble resin can be selected in a wider range by employing a ball-point pen tip of a metal or a resinous material at the pen tip, instead of a fiber bundle. As explained in the foregoing, a larger amount of addition of the water-soluble resin provides a better fixing property of the writing. Also a water-soluble resin of a high film forming property is selected as explained in the foregoing. To broaden the range of the water-soluble resin in light of the above is difficult in a writing utensil utilizing a fiber bundle as the pen tip, but can be realized by employing a ball-point pen chip of a metal or a resinous material as the pen tip. As an effect of such function, there is realized a fixing property of the writing on a non-permeable surface, not found as with the conventional marking pen.

In the ink composition, there may be added other additives, if desired, for example a surfactant such as a phosphoric acid ester for realizing an ink wetting or improving the feeling of writing on the non-permeable surface and an antirusting agent for obtaining an antirusting effect in case of employing a ball-point pen tip formed by a metal as the pen tip, also an antiseptic or an antimold agent such as 1,2-benzisothiazolin-3-one for preventing rotting of the aqueous ink, a wetting regulating agent such as water-soluble modified silicone oil for realizing a stable ink wetting on the non-permeable surface, and a fixing agent such as an acryl emulsion for further improving the fixing property of the writing on the non-permeable surface.

[0010]

[Examples]

In the following, the present invention will be clarified further by examples.

5 Example 1

Pigment Black 7	5.0 wt. %
water-soluble resin (acrylic resin component of trade name: HPD-96)	4.5 wt. %
isopropyl alcohol	7.0 wt. %
10 water	80.8 wt. %
antirusting lubricant (trade name: A-208S)	0.5 wt. %
triethanol amine	1.0 wt. %
fixing property improving agent (acryl emulsion component of trade name: Johncryl 7001)	0.8 wt. %
15 wetting property improving agent (trade name: KF-618)	0.2 wt. %
1,2-benzisothiazolin-3-one	0.2 wt. %

There were employed Pigment Black 7 as the pigment coloring agent, a water as the solvent, and an acrylic resin of a trade name HPD-96 (manufactured by Johnson Polymer Inc.) having a molecular weight of 16,500, 20 a glass transition point of 102°C and an acid value of 240 as the water-soluble resin having the pigment dispersing function and the writing fixing ability. These components were exactly weighed in predetermined amounts and the pigment was uniformly dispersed in a ball mill to obtain a pigment dispersion. Then triethanol amine as a pH regulating agent, 25 a phosphoric acid ester surfactant (trade name Prisurf A-208S,

manufactured by Dai-ichi Kogyo Seiyaku Co.) as the antirusting lubricant, an acrylic emulsion (trade name Johncryl 7001, manufactured by Johnson Polymer Inc.) as the improver of fixing property of the writing, a water-soluble modified silicone oil (trade name KF-618, manufactured by Shin-etsu Chemical Co.) as the improver of wetting properties on the non-permeable surface, and 1,2-benzisothiazolin-3-one as the antimold agent were exactly weighed in predetermined amounts, then agitated under heating for 1 hour at an agitating temperature of 50°C with a disper agitator and was then gradually cooled to a liquid temperature of 30°C. Then to the uniformly mixed liquid, under agitation in the disper, was gradually added isopropyl alcohol of a predetermined amount having a vapor pressure of 4.3 KPa at 20°C and the mixture was agitated for 20 minutes at 30°C to obtain a water based ink for ball-point pen, the ink showing a black color and producing a black writing. With respect to the components of the trade names HPD-96 and Johncryl 7001, the ink was designed in consideration of the respective effective solids thereof. Also the ink viscosity at 20°C was set to 5 mPa.s.

[0011]

Example 2

A water based ink for ball-point pen showing a green color and producing a green writing was prepared in the same manner as in Example 1, except for employing a green pigment Pigment Green 7 as the coloring material and also employing an acrylic resin (trade name Johncryl 60, manufactured by Johnson Polymer Inc.) having a molecular weight of 8,500, a glass transition point of 85°C and an acid value of 215 as the

water-soluble resin having the pigment dispersing function and the writing fixing ability, and following other formulations as shown in Table 1. With respect to the components of the trade names Johncryl 60 and Johncryl 7001, the ink was designed in consideration of the respective effective solids thereof.

[0012]

Example 3

A water based ink for ball-point pen showing a red color and producing a red writing was prepared in the same manner as in Example 1, except for employing a red pigment Pigment Red 170 as the coloring material and following other formulations as shown in Table 1. With respect to the components of the trade names HPD-96 and Johncryl 7001, the ink was designed in consideration of the respective effective solids thereof.

[0013]

Example 4

A water based ink for ball-point pen showing a black color and producing a black writing was prepared in the same manner as in Example 1, except for employing a styrene-maleic acid resin (trade name Arastar 703S, manufactured by Arakawa Kagaku Kogyo Co.) as the water-soluble resin, and a dispersing agent (trade name NIKKOL TL-10, manufactured by Nikko Chemicals Co.) and following other formulations as shown in Table 1. With respect to the components of the trade names Araster 703S and Johncryl 7001, the ink was designed in consideration of the respective effective solids thereof.

[0014]

Example 5

A water based ink for ball-point pen showing a black color and producing a black writing was prepared in the same manner as in Example 1, except for employing as the solvent ethanol having a vapor pressure at 20°C of 5.9 KPa and following other formulations as shown in Table 1. With respect to the components of the trade names Johncryl 60 and Johncryl 7001, the ink was designed in consideration of the respective effective solids thereof.

[0015]

10 Example 6

A water based ink for ball-point pen showing a black color and producing a black writing was prepared in the same manner as in Example 1, except for increasing the amount of the water-soluble resin of the trade name HPD-96 and following other formulations as shown in Table 2. With respect to the components of the trade names HPD-96 and Johncryl 7001, the ink was designed in consideration of the respective effective solids thereof.

[0016]

Examples 7 - 9

20 Water based inks for ball-point pen showing a black color and producing a black writing were prepared in the same manner as in Example 1, except for eliminating the antirusting lubricant in Example 7, the fixing property improving agent in Example 8 and the wetting property improving agent on the non-permeable surface in Example 9, and following
25 other formulations as shown in Table 2.

[0017]

Example 10

A ball-point pen 1 is a direct filling ball-point pen directly containing the ink composition 7 of Example 1 in an ink tube 2 consisting of a shaft tube, and a ball-point pen tip 4 formed by a stainless steel material and rotatably supporting a ball 5 is provided across a tip holder 3 at a front end of the ink tube 2.

In the ink tube 2, an ink following member 8 of grease state, capable of following the consumption of the ink, is directly charged in contact with an ink surface, at a tail end portion (at a side of a tail cap 6) opposite to the mounting part of the ball-point pen tip.

[0018]

Comparative Examples 1 - 7

Water based inks for ball-point pen were prepared in the same manner as in Example 1, except for employing ink compositions as shown in Tables 3 and 4.

The ink viscosity was measured with a viscosimeter Model B8M, manufactured by Tokimec Co., at a revolution of a BL rotor of 12 rpm and under an environment of 20°C.

The Examples and the Comparative Examples are shown in following tables.

[0019]

Table 1

Example		1	2	3	4	5
Pigment	Pigment Black 7	5.0	—	—	5.0	5.0
	Pigment Green 7	—	7.0	—	—	—
	Pigment Red 170	—	—	7.0	—	—
Water-soluble resin	Johncryl 60 (acryl resin component)	—	5.1	—	—	17.0
	HPD-96 (acryl resin component)	4.5	—	12.0	—	—
	Arastar 703S (styrene-maleic acid resin component)	—	—	—	12.0	—
Dispersant	NIKKOL TL-10 (polyoxyethylene sorbitan fatty acid ester)	—	—	—	3.0	—
Solvent	isopropyl alcohol	7.0	7.0	7.0	7.0	—
	ethanol	—	—	—	—	7.0
	water	80.8	78.2	71.3	70.3	68.3
Antirusting lubricant	A-208S (phosphate ester surfactant)	0.5	0.5	0.5	0.5	0.5
pH regulating agent	triethanol amine	1.0	1.0	1.0	1.0	1.0
Fixation improving agent	Johncryl 7001 (acryl emulsion component)	0.8	0.8	0.8	0.8	0.8
Wetting regulating agent	KF-618 (water-soluble modified silicone oil)	0.2	0.2	0.2	0.2	0.2
Antimold agent	1,2-benzisothiazolin-3-one	0.2	0.2	0.2	0.2	0.2
Ink viscosity		5.0	5.0	20.0	20.0	30.0
Writing ability on non-permeable surface		◎	◎	◎	◎	○
Drying of writing on non-permeable surface		○	○	◎	○	◎
Fixing of writing on non-permeable surface		○	○	◎	○	◎
Covering power of writing on non-permeable surface		◎	◎	◎	◎	◎
Blotting of writing on paper		○	○	◎	○	◎
Ink drying-up at pen tip		◎	◎	◎	◎	○

[0020]

Table 2

Example		6	7	8	9	
Pigment	Pigment Black 7	5.0	5.0	5.0	5.0	
	Pigment Green 7	-	-	-	-	
	Pigment Red 170	-	-	-	-	
Water-soluble resin	Johncryl 60 (acryl resin component)	-	-	-	-	
	HPD-96 (acryl resin component)	7.0	12.0	12.5	12.0	
	Arastar 703S (styrene-maleic acid resin component)	-	-	-	-	
Dispersant	NIKKOL TL-10 (polyoxyethylene sorbitan fatty acid ester)	-	-	-	-	
Solvent	isopropyl alcohol	7.0	7.0	7.0	7.0	
	ethanol	-	-	-	-	
	water	78.3	74.3	73.6	73.5	
Antirusting lubricant	A-208S (phosphate ester surfactant)	0.5	-	0.5	0.5	
pH regulating agent	triethanol amine	1.0	0.5	1.0	1.0	
Fixation improving agent	Johncryl 7001 (40) (acryl emulsion component)	0.8	0.8	-	0.8	
Wetting regulating agent	KF-618 (water-soluble modified silicone oil)	0.2	0.2	0.2	-	
Antimold agent	1,2-benzisothiazolin-3-one	0.2	0.2	0.2	0.2	
Ink viscosity		10.0	20.0	20.0	20.0	
Writing ability on non-permeable surface		◎	○	◎	○	
Drying of writing on non-permeable surface		◎	◎	○	○	
Fixing of writing on non-permeable surface		◎	○	○	○	
Covering power of writing on non-permeable surface		◎	◎	◎	◎	
Blotting of writing on paper		○	◎	◎	○	
Ink drying-up at pen tip		◎	◎	◎	◎	

[0021]

Table 3

Comparative Example			1	2	3	4	5
Coloring material	Pigment	Pigment Black 7	5.0	5.0	5.0	5.0	—
	Dye	Direct Black 154	—	—	—	—	7.0
Water-soluble resin		HPD-96 (acryl resin component)	3.0	18.0	12.0	—	12.0
Dispersant		NIKKOL TL-10 (polyoxyethylene sorbitan fatty acid ester)	—	—	—	3.0	—
Solvent	ethylene glycol		—	—	5.0	—	—
	isopropyl alcohol		7.0	7.0	—	7.0	7.0
	water		82.3	67.3	75.3	82.3	71.3
Antirusting lubricant		A-208S (phosphate ester surfactant)	0.5	0.5	0.5	0.5	0.5
pH regulating agent		triethanol amine	1.0	1.0	1.0	1.0	1.0
Fixation improving agent		Johncryl 7001 (acryl emulsion component)	0.8	0.8	0.8	0.8	0.8
Wetting regulating agent		KF-618 (water-soluble modified silicone oil)	0.2	0.2	0.2	0.2	0.2
Antimold agent		1,2-benzisothiazolin-3-one	0.2	0.2	0.2	0.2	0.2
Ink viscosity			3.0	35.0	20.0	3.0	20.0
Writing ability on non-permeable surface			◎	×	△	◎	×
Drying of writing on non-permeable surface			×	—	×	×	—
Fixing of writing on non-permeable surface			×	—	×	×	—
Covering power of writing on non-permeable surface			×	—	×	×	—
Blotting of writing on paper			×	◎	×	×	×
Ink drying-up at pen tip			△	×	○	△	×

[0022]

Table 4

Comparative Example			6	7			
Coloring material	Pigment	Pigment Black 7	5.0	5.0			
	Dye	Direct Black 154	—	—			
Water-soluble resin	HPD-96 (acryl resin component)		—	12.0			
	Arastar 703S (styrene-maleic acid resin component)		2.5	—			
Dispersant	NIKKOL TL-10 (polyoxyethylene sorbitan fatty acid ester)		—	—			
Solvent	ethylene glycol		—	3.0			
	isopropyl alcohol		7.0	7.0			
	water		81.6	69.1			
Antirusting lubricant	A-208S (phosphate ester surfactant)		0.5	0.5			
pH regulating agent	triethanol amine		1.0	1.0			
Fixation improving agent	Johncryl 7001 (acryl emulsion component)		2.0	2.0			
Wetting regulating agent	KF-618 (water-soluble modified silicone oil)		0.2	0.2			
Antimold agent	1,2-benzisothiazolin-3-one		0.2	0.2			
Ink viscosity			3.0	20.0			
Writing ability on non-permeable surface			◎	◎			
Drying of writing on non-permeable surface			×	×			
Fixing of writing on non-permeable surface			×	×			
Covering power of writing on non-permeable surface			×	×			
Blotting of writing on paper			×	×			
Ink drying-up at pen tip			△	△			

[0023]

Also the shape and the structure of the ball-point pen tip are not limited to those in the foregoing example, and it is preferable, for

5 improving the prevention of ink leakage, to incorporate a valve mechanism (not shown in the figure) where the ball, rotatably supported in the pen tip is pressed to an internal wall of a pen tip ridge by a coil spring disposed in pressure contact with a rear end of the ball either directly or across a pressing member while not in use, and a gap is formed between

the internal wall of the pen tip ridge and the ball by a thrust applied at a writing whereby allowing the ink to flow out.

Also the ball 8 to be employed in the present invention may be an ultra hard ball formed by an ultra hard material such as tungsten carbide, or a ceramic ball such as of silica, alumina, zirconia or silicon carbide, but, in order that the ball rotates also on a non-permeable surface such as metal, glass or plastics, a smaller rotation resistance is preferable between the ball and the ball seat surface as explained before. It is therefore preferable to employ a ceramic ball or a so-called mirror surface ball having a surface roughness of 5 nm or less in terms of the arithmetic mean roughness (Ra) and showing a low rotation resistance between the ball and the ball seat surface. The arithmetic mean roughness (Ra) is obtained, as indicated by a following equation 1, by extracting from a roughness curve, measured by a surface roughness measuring instrument of stylus method (model: Form-Talsurf-S1F-50, manufactured by Taylor-Hobson Inc.) a reference length L in a direction of an average line, and summing the absolute value of a deviation from the average line to the curve within the extracted portion to determine the average.

[0024]

20 Equation 1

$$Ra = 1 / L * \int_0^L |f(x)|$$

[0025]

Testing methods and evaluations

Each of the water based inks for ball-point pen of Examples 1 - 9 and Comparative Examples 1 - 7 was evaluated and directly filled in the

ink tube 2 of Example 10 to prepare a ball-point pen 1, which was evaluated in following tests.

(1) Writing ability on non-permeable surface

Writing on an untreated glass surface was evaluated:

5 ⊙ specifications providing extremely satisfactory performances both in ink flow-out and writing;

 ○ specifications providing satisfactory performance in writing;

 △ specifications capable of writing but with certain line
10 interruption;

 × specifications incapable of writing.

(2) Drying of writing on non-permeable surface

1 g of ink was dropped on a glass plate and was squeezed to an ink film thickness of 10 μ m, and the state of the ink film was observed and
15 evaluated under a test environment of $23 \pm 2^\circ\text{C}$ and a humidity of $50 \pm 5\%$ RH:

 ⊙ specifications providing complete drying of the ink film less than 20 seconds;

 ○ specifications providing complete drying of the ink film
20 within 20 to 30 seconds;

 △ specifications providing complete drying of the ink film
within 40 to 50 seconds;

 × specifications requiring 60 seconds or more for ink drying.

(3) Fixation of writing on non-permeable surface

1 g of ink was dropped on a glass plate, then was squeezed to an
25 ink film thickness of 10 μ m, was allowed to stand for 10 minutes in a test

environment of $23 \pm 2^{\circ}\text{C}$ and a humidity of $50 \pm 5\% \text{RH}$, and was rubbed 10 times with a cotton cloth under a load of 100 gf/cm^2 , and the state of the dried ink film thereafter was observed:

5 ⊙ specifications showing no peeling at all of the dried ink film;

 ○ specifications showing a very slight damage on the ink film;

 △ specifications showing a damage on the ink film;

 × specifications showing a damage in a half or more of the ink film.

10 (4) Covering power of writing on non-permeable surface

 1 g of ink was dropped on a glass plate and was squeezed to an ink film thickness of $10 \mu\text{m}$, then the glass plate was placed on a printed character and an observation was made to judge whether the printed character is legible.

15 ⊙ ink specifications covering the glass surface, so that the underlying printed character was not legible at all;

 ○ ink specifications producing the results that the underlying printed character was slightly detectable as a trace;

 × ink specifications producing the results that the
20 underlying printed character was clearly legible.

(5) Blotting of writing on paper surface

 A straight line was drawn on a writing paper A (JIS P3201) in a test environment of $23 \pm 2^{\circ}\text{C}$ and a humidity of $50 \pm 5\% \text{RH}$, and under conditions of a writing load of 100 gf and a writing speed of 4 m/min ,
25 and a blotting generated on the writing was observed:

- ◎ extremely satisfactory writing without any blotting;
- writing with practically acceptable blotting;
- △ writing with somewhat unacceptable blotting;
- × writing with very unacceptable blotting.

5 (6) Ink drying-up on pen tip

The pen was allowed to stand for 24 hours in a cap-off state in an environment of 23°C and a humidity of 50 %RH, then a straight line was drawn on a writing paper A (JIS P3201) under a writing load of 100 gf and a state at the start of writing was observed:

- 10 ◎ specifications providing a satisfactory writing within 2 cm from the start of writing;
- specifications providing a satisfactory writing in 2 - 4 cm from the start of writing;
- △ specifications providing a satisfactory writing in 5 - 7
- 15 cm from the start of writing;
- × specifications not providing a satisfactory writing after 7 cm or more from the start of writing.

(Evaluation)

Comparative Example 1 provided an ink with an excessively low ink

20 viscosity of 3 mPa.s. It was capable of satisfactory writing on the non-permeable surface, but showed an evident blotting on the paper surface because of an excessively low ink viscosity. Also because of the excessively low ink viscosity, the ink flow-out control at the pen tip did not function satisfactorily to result in an excessive ink flow-out,

25 thus deteriorating the drying property of writing and the fixation of

writing.

Comparative Example 2 provided an ink with an excessively high ink viscosity of 35 mPa.s. Because of the excessively high ink viscosity, it was incapable of satisfactory writing on the non-permeable surface and
5 was therefore excluded from the evaluation.

Comparative Example 3 employed a water and ethylene glycol having a vapor pressure at 20°C of 7.0×10^{-4} KPa as the solvent. Because of a significantly lowered drying property of the ink, the results were inferior in terms of the drying property of writing, the fixation of
10 writing and the blotting of writing on paper surface.

Comparative Example 4 provided a formulation designed to disperse the pigment by a surfactant, without employing a water-soluble resin. Although the writing on the non-permeable surface was possible, the results were significantly inferior in terms of the drying property of
15 writing, the fixation of writing and the blotting of writing.

Comparative Example 5 provided a formulation employing a dye instead of a pigment. Because the ink drying at the pen tip proceeded rapidly into the interior of the pen tip, a sufficient writing performance could not be obtained on the non-permeable surface and it was excluded
20 from the evaluation. Also, though it was capable of satisfactory writing on paper, the writing showed an evident blotting because of a strong penetrability of the writing.

Comparative Example 6 employed a styrene-maleic acid resin instead of the acrylic resin, but provided performances similar to those of
25 Comparative Example 1 because of an excessively low ink viscosity as in

Comparative Example 1.

Comparative Example 7 employed a combination of water, ethylene glycol having a vapor pressure at 20°C of 7.0×10^{-4} KPa, and isopropyl alcohol having a vapor pressure at 20°C of 4.3 KPa as the solvent. Because
5 the properties of ethylene glycol were apparently exhibited, the results were inferior in terms of the drying property of writing, the fixation of writing and the blotting of writing on paper.

When the water based inks for ball-point pen of Examples 1 to 9 were employed in a marking pen having a pen tip formed with a fiber bundle,
10 though such examples being not described in the tables nor illustrated, Examples 3 to 9 were incapable of writing because of an excessively high ink viscosity. Also Examples 1 and 2 showed complete drying at the pen tip, and were incapable of writing due to poor ink drying-up performance.
[0026]

15 [Effects of the Invention]

The present invention provides an excellent effect of enabling writing also on a non-permeable surface owing to a particular ink composition.

[Brief Description of the Drawing]

20 [Fig. 1] This is a schematic view of a ball-point pen using water based ink of the present invention.

[Description of Reference Numerals]

- 1 Ball-point pen
- 2 Ink tube
- 25 3 Tip holder

- 4 Ball-point pen tip
- 5 Ball
- 6 Tail cap
- 7 Ink
- 5 8 Ink following member

[Document Name] Abstract

[Abstract]

[Object] The invention is to provide a water based ink for ball-point pen capable of writing also on a non-permeable surface and ball-point pen using a same ink.

[Means for Solving Problems] There are provided a water based ink for ball-point pen including a solvent formed by a water and an alcoholic solvent having a vapor pressure at 20°C of 0.5 kPa or higher, a pigment constituting a coloring material, a water-soluble resin constituting a writing fixing agent, and a surfactant of phosphoric acid ester type wherein an ink viscosity at 20°C is within a range of 5 to 30 mPa·s, and a ball-point pen using the same ink.

[Selected Figure] Fig. 1